Check for updates

OPEN ACCESS

EDITED AND REVIEWED BY Tomas Ramirez Reina, University of Surrey, United Kingdom

*CORRESPONDENCE Muwei Ji, jimuwei@163.com Jintao Huang, jintao.huang@gdut.edu.cn Guangtao Cong, gtcong@szu.edu.cn

[†]These authors have contributed equally to this work

SPECIALTY SECTION

This article was submitted to Catalytic Reactions and Chemistry, a section of the journal Frontiers in Chemistry

RECEIVED 02 November 2022 ACCEPTED 04 November 2022 PUBLISHED 18 November 2022

CITATION

Lin J, Wei H, Su J, Li X, Huang J, Anwer S, Liang S, Cong G, Xu L, Lu F and Ji M (2022), Editorial: Functional units of nanocrystals: Synthesis, tailoring, and applications. *Front. Chem.* 10:1087379. doi: 10.3389/fchem.2022.1087379

COPYRIGHT

© 2022 Lin, Wei, Su, Li, Huang, Anwer, Liang, Cong, Xu, Lu and Ji. This is an open-access article distributed under the terms of the Creative Commons Attribution License (CC BY). The use, distribution or reproduction in other forums is permitted, provided the original author(s) and the copyright owner(s) are credited and that the original publication in this journal is cited, in accordance with accepted academic practice. No use, distribution or reproduction is permitted which does not comply with these terms.

Editorial: Functional units of nanocrystals: Synthesis, tailoring, and applications

Jiahui Lin^{1†}, Huixian Wei^{2†}, Jingtao Su¹, Xinyuan Li³, Jintao Huang^{1*}, Shoaib Anwer⁴, Shuyu Liang⁵, Guangtao Cong⁶*, Linli Xu⁷, Fushen Lu² and Muwei Ji²*

¹Department of Polymeric Materials and Engineering, School of Materials and Energy, Guangdong University of Technology, Guangzhou, China, ²College of Chemistry and Chemical Engineering, Chemistry Department, Shantou University, Shantou, China, ⁵MOE Key Laboratory of Cluster Science, School of Chemistry and Chemical Engineering, Beijing Institute of Technology, Beijing, China, ⁴Department of Mechanical Engineering, College of Engineering, Khalifa University, Abu Dhabi, United Arab Emirates, ⁵Sika Aktien Aktien Gesellschaft (AG), Baar, Switzerland, ⁶Institute of Low-Dimensional Materials Genome Initiative, College of Chemistry and Environmental Engineering of Shenzhen University, Shenzhen, China, ⁷Department of Applied Biology and Chemical Technology, The Hong Kong Polytechnic University Shenzhen Research Institute, The Hong Kong Polytechnic University, Hong Kong SAR, China

KEYWORDS

functional units, nanocrystals, synthesis, tailoring, applications

Editorial on the Research Topic Editorials: Functional units of nanocrystals: Synthesis, tailoring, and applications

Functional materials with special structural units are explored to acquire excellent properties; highly ordered functional units of atomic or molecular sizes would provide a high effective atom utilization and a superior functional synergetic effect. For functional materials, their active sites, or main functional structures, can be defined by defects, highindex facets, single-atom catalytic sites with coordinated surroundings, doping sites, heterostructure interfaces, frameworks, etc. Herein, these sites or structures are further defined as functional units with sizes ranging from more than 10 p.m. (such size may be one atom) to sub-micrometer, often determining their capacities for catalysis, energy conversion and storage, and luminescence (Lu and Yin, 2012; Gaitzsch et al., 2016; Cao et al., 2022). We hope that "functional units" are helpful to more clearly explain structureproperty relationships, providing additional possibilities for designing and developing new materials with novel functionalities. For example, single-atom sites for catalysis and new frameworks for harvesting solar energy are considered functional units. Nowadays, various functional units have been proposed in different fields for exploring materials with significantly enhanced functional properties; however, it is difficult to characterize confined structures and to reveal functional relationships between structures.

Li and coauthors reviewed the atomic surface modulation of 2D semiconductors for enhancing photocatalysis; discussing vacancies, single atom-doping, and dual-site components. For 2D semiconductor photocatalysts, there are several effective paths to promote their

performance. Li et al. first focused on vacancy modulation in various 2D semiconductors to tune the band gap and to enhance charge transfer during photocatalysis. Either modulating the band gap or enhancing charge transfer reduced the number of photo-generated electrons and holes, which play a key role in photocatalysis. Photocatalysis was also enhanced by introducing single-atom sites that shorten the migration distance of photo-generated charges. More importantly, these introduced single atoms are widely accepted as efficient photocatalytic sites. Meanwhile, catalytic sites in 2D semiconductors were also modulated to form dual sites: metalmetal or metal-vacancies sites. The metal-metal dual site on the surface of 2D semiconductors allowed modulation of the d band center and its position relative to the Fermi level, which affected the absorption energy of the reactive metal and facilitates electron transfer. Metal single-atom loading also resulted in metal-vacancy dual sites for catalysis, and the coupling effect between the metal and the vacancy promoted photocatalysis selectivity. Separating the photo-generated electrons and holes is crucial in photocatalysis and constructing such functional units for enhancing the photocatalysis remains a major challenge.

Iqbal et al. reported $ZnFe_2O_4/S-g-C_3N_4$ with high photocatalytic activity obtained by boosting the separation of photo-generated electrons and holes. The proposed heterostructure facilitated photo-generated charge transfer and thus enhanced photo-degradation and antimicrobial performances. This work on constructing heterostructures for promoting photocatalysis also illustrates the importance of interface structure in accelerating electron and hole transfer.

Xing and coworkers proposed different scenarios for catalysis, based on the interaction interface between a metal and carbon. The authors described four types of metal-carbon interfaces and their capacities for catalysis. Regarding the metal-carbon interaction surface, generated using large metal nanoparticles, the carbon support played a role in preserving the aggregation of metal NPs and the catalytic activity depended on the metal components. In the case of single-atom catalysts, the carbon support provided a coordination microenvironment for the metal atom, and limited the catalytic activity. For metal@carbon core-shell catalysts, electrons in the metal were transferred to carbon, and the structure allowed maintenance of the high activity of metal nanoparticles, thereby preventing corrosion in harsh environments. Meanwhile, the metalcarbon interface formed a Mott-Schottky junction that also modulated electron transfer and therefore the associated catalytic activities. These works clearly presented well-defined interfaces for promoting catalysis.

References

Zhang et al. prepared Pt-based nanosheets to enhance the hydrogenation catalysis of olefins and nitrobenzene. The high performances originated from the high surface area of the Pt nanosheets as well as the interconnected network, which provided a high concentration of active sites. The TOFs of the as-prepared Pt nanosheets were three times higher than those of homemade Pt nanoparticles. The morphologies and the interconnected sites were considered key structures for hydrogenation catalysis. Although the authors did not indicate the functional units for catalysis, hydrogenation sites were conceived to be dependent on the unique structure.

This Research Topic for Frontiers in Chemistry aims to navigate structural units for promoting catalytic activities. Besides catalysts, functional units are also expected to be applied in other functional materials. Last but not least, we believe that this topic will educate readers and inspire scientists working in the fields of chemistry and materials engineering to identify and investigate structural units that influence the associated functions.

Author contributions

JL: Writing—Original Draft. HW: Writing—Original Draft. JS: Validation. XL: Data curation. JH: Funding acquisition, Writing-Review and Editing. SA: Investigation. SL: Investigation. GC: Funding acquisition. LX: Investigation. FL: Supervision. MJ: Supervision, Writing-Review and Editing.

Conflict of interest

The authors declare that the research was conducted in the absence of any commercial or financial relationships that could be construed as a potential conflict of interest.

Publisher's note

All claims expressed in this article are solely those of the authors and do not necessarily represent those of their affiliated organizations, or those of the publisher, the editors and the reviewers. Any product that may be evaluated in this article, or claim that may be made by its manufacturer, is not guaranteed or endorsed by the publisher.

Cao, Y., Weng, M., Mahmoud, M. H. H., Elnaggar, A. Y., Zhang, L., El Azab, I. H., et al. (2022). Flame-retardant and leakage-proof phase change composites based on MXene/polyimide aerogels toward solar thermal energy harvesting. *Adv. Compos. Hybrid. Mat.* 5, 1253–1267. doi:10.1007/s42114-022-00504-4

Gaitzsch, J., Huang, X., and Voit, B. (2016). Engineering functional polymer capsules toward smart nanoreactors. *Chem. Rev.* 116, 1053–1093. doi:10.1021/acs.chemrev.5b00241

Lu, Z., and Yin, Y. (2012). Colloidal nanoparticle clusters: functional materials by design. *Chem. Soc. Rev.* 41, 6874–6887. doi:10.1039/C2CS35197H